

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
30 October 2003 (30.10.2003)

PCT

(10) International Publication Number
WO 03/089508 A1(51) International Patent Classification⁷: **C08K 3/22**

(21) International Application Number: PCT/US03/11941

(22) International Filing Date: 16 April 2003 (16.04.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/374,014 19 April 2002 (19.04.2002) US(71) Applicant (*for all designated States except US*): **SAINT-GOBAIN CERAMICS & PLASTICS, INC.** [US/US];
1 New Bond Street, Box Number 15138, Worcester, MA
01615-0138 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **BAUER, Ralph**
[CA/CA]; 6913 Cumberland Court, Niagara Falls, Ontario
L2H 4R6 (CA). **MIRLEY, Christopher, L.** [US/US]; 34
Boylston Circle, Shrewsbury, MA 01545 (US). **TANG,**
Hui [CN/CN]; 11G Goldthwaite Road, #2, Worcester, MA
01605 (US).(74) Agents: **BUJOLD, Michael, J.**; Davis and Bujold,
P.L.L.C., Fourth Floor, 500 North Commercial Street,
Manchester, NH 03101 et al. (US).(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN,
YU, ZA, ZM, ZW.(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

**WO 03/089508 A1**

(54) Title: NOVEL BOEHMITE PARTICLES AND POLYMER MATERIALS INCORPORATING SAME

(57) Abstract: A modified polymer material is disclosed, including a polymer base and boehmite particles provided in the polymer base. The boehmite particles are made up of mainly anisotropically shaped particles.

WO 03/089508

PCT/US03/11941

1

NOVEL BOEHMITE PARTICLES AND POLYMER MATERIALS INCORPORATING SAME

BACKGROUND OF THE INVENTION

Field of the Invention

- [01] The present invention concerns particles of boehmite and particularly to boehmite particles that are particularly adapted to use as fillers for thermoplastic resins.

Description of the Related Art

- [02] Boehmite has long been recognized as a suitable filler for thermoplastic resins in view of the fine particle size and the relative inertness to the polymer in which it is dispersed. It produces good improvements in modulus and thermal behavior and has even been proposed as a flame retardant in USP 6,143,816.
- [03] The preferred form as recited in a number of US Patents such as USP 5,360,680 and 5,401,703 is that of fine flakes which were felt to be preferable since earlier fine grained boehmite powders produced by a milling process tended to be globular which is less effective as a filler material. Other methods of making fine boehmite particles caused other problems. For example pyrolysis tends to produce a range of contaminants of the boehmite product and conventional hydrothermal treatments tend to produce tight agglomerates of rhombic prisms which are not easily separated. Refined hydrothermal treatments of aluminum hydroxides such as that of USP 5,194,243, (which built on earlier work described in USPP 2,763,620; 2,915,475; 3,385,663; 4,117,105; and 4,344,928), introduced the concept of seeding the conversion of the boehmite pre-cursor using boehmite seeds. This was found to require a high level of seeding to be effective using at least 15% of boehmite seed in order to produce a sub-micron boehmite dispersion with essentially equiaxed particles.
- [04] All such efforts produced flaky or equiaxed particles of boehmite which did not readily disperse as individual particles in a polymer unless previously treated with a surface active agent designed to enhance such dispersibility. Typical surface active agents used include amino-silanes which have the capability of bonding to the hydrophilic surfaces of the particles giving them a surface more compatible with the organic polymer in

WO 03/089508

PCT/US03/11941

- 2 -

which they were to be dispersed. This avoided the clumping that tended to occur without such a treatment. This tendency becomes greater with decreasing size of the particles because of the increasing surface energy that naturally occurs with diminishing size.

- [05] The present invention provides a novel form of boehmite that can be readily dispersed in a thermoplastic polymer at the nano-particle level without the need for any surface treatment and which provide a significantly improved blend of properties by comparison with the prior art boehmite filler materials.

SUMMARY

- [06] According to one aspect of the present invention, a modified polymer material is provided, which includes a polymer base and boehmite particles provided in the polymer base, the boehmite particles comprising mainly anisotropically shaped particles having an aspect ratio of at least about 3:1.
- [07] According to another aspect of the present invention, a modified polymer material is provided, which includes a polymer base and boehmite particles free of surface agents and being dispersed in the polymer base.
- [08] According to another aspect of the present invention, a boehmite material is provided, having mainly boehmite particles having an aspect ratio of at least about 3:1.
- [09] According to another aspect of the present invention, a method for forming a product is provided, including providing a modified polymer material having a polymer base and boehmite particles containing mainly anisotropically shaped particles having an aspect ratio of at least about 3:1, and extruding the modified polymer material to form an extruded product, wherein the boehmite particles are dispersed in the extruded product.

BRIEF DESCRIPTION OF THE DRAWINGS

- [10] Figures 1A and 1B show prior art finely dispersed boehmite particles (Figure 1A) and needle-shaped boehmite according to the invention (Figure 1B).

WO 03/089508

PCT/US03/11941

- 3 -

- [11] Figures 2A, 2B and 2C show the UV-visible Spectra of: Nylon 6 alone and with two different levels of boehmite incorporation.
- [12] Figures 3A, 3B and 3C are Fourier Transform IR spectra of the three formulations for which the UV spectra are given in Figures 2A, 2B and 2C.
- [13] Figure 4 shows the corresponding N 1s spectra for the same three formulations.
- [14] Figure 5 shows a high magnification transmission electron micrograph of Nylon 6 with 6.62 vol% of boehmite.
- [15] Figures 6A and 6B show bar graphs for different physical properties relating to nylon 6 alone, with 3.15vol% of conventional boehmite, and with 3.15vol% of the needle-shaped boehmite of the invention.
- [16] Figure 7 shows a high magnification transmission electron micrograph of a thermoplastic polyurethane (Isoplast 301 sold by Dow Chemical Company), with 1.86 vol% of boehmite.
- [17] Figure 8 is a bar graph showing the effect of amino-silane additives in improving the storage modulus of an epoxy resin having 5vol% of needle-shaped boehmite particles dispersed therein.

DETAILED DESCRIPTION

- [18] The present invention provides boehmite particles comprising needle-shaped, (or anisotropic), crystals in which the longest dimension is at least 50 nanometers and preferably from 50 to 2000, and more preferably from 100 to 1000, nanometers; and the dimensions perpendicular to the length are essentially the same and are each less than 50 nanometers; and the aspect ratio, defined as the ratio of the longest dimension to the next largest dimension perpendicular to the length, is at least 3: 1, and preferably at least 6:1. These particles will henceforth be described as "needle-shaped" in this description for the sake of clarity.
- [19] Unexpectedly the hydrothermal conditions combined with the relatively low seeding level and the acidic pH of the mixture, resulted in preferential growth of the boehmite

WO 03/089508

PCT/US03/11941

- 4 -

along one axis such that, the longer the hydrothermal treatment continued, the longer were the needle-shaped boehmite particles that were produced. Remarkably these needle-shaped boehmite particles require no surface treatment to be individually and uniformly dispersed, that is to say to give an essentially uniform distribution within the polymer substantially without forming aggregates, by conventional compounding processes. This uniform and individual dispersion quality is hereinafter called "nano-dispersibility".

- [20] The needle-shaped particles according to the invention have a surface area, as measured by the BET technique, of at least $75\text{m}^2/\text{g}$, and preferably from 100 to $300\text{m}^2/\text{g}$.
- [21] The invention also includes polymers modified by the incorporation of from 0.5 to 20%, and preferably from 2 to 10%, by volume (based on the combined volume of polymer plus boehmite), of the needle-shaped boehmite particles of the invention. The polymers in which the needle-shaped boehmite particles can be dispersed include for example polyamides, (including for example nylon 6 and nylon 12), thermoplastic polyurethanes, polyalkylene-glycols, ethylene/vinyl alcohol polymers, epoxy resins, acrylate based resins and the like. More generally the polymers are preferably thermoplastic polymers because this takes advantage of the very good dispersibility used in conventional polymer compounding technology using high intensity mixers, extruders and the like. It also recognizes that the use of fillers in the modification of physical properties of a polymer is most frequently an objective in the field of thermoplastic polymers. The products of this invention have the unique property (probably a function of their needle shapes) such that, upon extrusion, the boehmite particles tend to become aligned such that a polymer reinforced by such needle-shaped particles will have considerably enhanced physical properties, such as flex strength, in the direction of extrusion.
- [22] It is believed that this unique dispersibility property of the needle-shaped boehmite particles derives from their ability to form hydrogen bonds with polar groups on the polymer chains which favors the mono-dispersed state. The needle-shaped boehmite particles can also be dispersed in other polymers which are essentially non-polar with the addition of conventional dispersing agents such as the amino-silanes.

WO 03/089508

PCT/US03/11941

- 5 -

- [23] Because thermosetting resins such as phenolic and acrylate-based resins are also polar in character, it is believed that the needle-shaped boehmite particles can be fully dispersed to the individual particle level in such polymers, if the incorporation is accomplished before the cross-linking stage is significantly advanced for example with the ingredients that form the polymer or at the B-Stage of a condensation resin such as a phenolic resin.
- [24] The needle-shaped boehmite particles according to the invention can be prepared by a hydrothermal treatment in which a boehmite precursor is dispersed/suspended in water and heated at a temperature of from 100 to 300 and preferable from 150 to 250°C in an autoclave at an autogenously generated pressure of from 1×10^5 to 8.5×10^6 and preferably from 5×10^5 to 1.2×10^6 newtons/m² for a period of from 1 to 24 and preferably from 1 to 3 hours. The % solids content of boehmite precursor in the dispersion is from 5 to 40, and preferably from 10 to 30 %. Along with the boehmite precursor, the dispersion comprises from 2 to 15 and preferably from 5 to 10 wt.%, based on the weight of the precursor, of boehmite particles. The boehmite particles act as seeds around which boehmite generated by conversion of the precursor, can crystallize. Because of the conditions of the hydrothermal treatment and the relatively low level of seeding, these crystals of boehmite grow preferentially along a single axis and to assume needle shapes which remain individually dispersed.
- [25] The boehmite precursor can be any aluminum trihydroxide such as bayerite or gibbsite but it can also be finely crushed bauxite. It is also possible to use gamma alumina as the starting material. In the event an impure material such as bauxite is used to produce the needle-shaped boehmite particles it may be desirable, prior to incorporating obtained the boehmite particles obtained into a polymer, to wash them to flush away impurities such as silicon or titanium hydroxides and at least some of the silica content which are the residue of common impurities occurring in natural bauxite ores.
- [26] Besides the unexpectedly easy and complete nano-dispersibility in polymers having polar groups, the needle-shaped particles of boehmite are easily dispersed in other polymers after receiving a suitable surface treatment with a surface active agent such as an amino-silane for example A-1100 which is commercially available from Aldrich Chemicals.

WO 03/089508

PCT/US03/11941

- 6 -

- [27] Because of the nano-dispersibility of the particles and their very small dimensions, the incorporation of such filler particles has minor or virtually no impact on the transparency of a thin film of the polymer, even at incorporation levels of up to 10vol%. This can prove a very valuable property in certain circumstances. It also means that thin-wall injection moldings can easily be obtained with points of weakness or surface interruptions-resulting from intrusions of particle agglomerates being largely eliminated.
- [28] After the hydrothermal process it is often advantageous to separate any unreacted material and any hard aggregates. This can usually be done by a simple centrifugation process or even by simply decanting the liquid phase containing the peptized boehmite from a precipitated or unreacted phase.

Preparation of the Needle-Shaped Boehmite

Example 1

- [29] An autoclave was charged with 250g of CV3002 gibbsite purchased from Alcoa; 25g of boehmite obtained from SASOL under the name- Catapal B pseudoboehmite; 1000g of deionized water; and 56g of 18% nitric acid. The boehmite was pre-dispersed in 100g of the water and 7 g of the acid before adding to the gibbsite and the remaining water and acid.
- [30] The autoclave was heated to 180°C over a 45 minute period and maintained at that temperature for 2 hours with stirring at 530 rpm. An autogenously generated pressure of about 150 psi was reached and maintained. Thereafter the boehmite dispersion was removed from the autoclave and the liquid content was removed at a temperature of 95°C. The resultant mass was crushed to less than 100 mesh.
- [31] The boehmite obtained was in needle-shaped particles as shown in Figure 1B. This is shown together with Figure 1A which illustrates the prior art boehmite as represented by C-200 boehmite from SASOL. It will be noted that C-200, in common with most commercial boehmite powders, has particles that are predominantly equiaxed, (equal dimensions in the three mutually perpendicular directions), except for some obvious agglomerates. Needle-shaped crystals are rare. By contrast the particles of the invention

WO 03/089508

PCT/US03/11941

- 7 -

are essentially all individual and needle-shaped, about 10-20 nanometers in diameter and about 100-200 nanometers in length.

Example 2

- [32] This example illustrates the technique used to blend the boehmite of the invention with nylon 6 and the properties of the products obtained at two different levels of incorporation of boehmite in comparison with the unmodified polymer.
- [33] Granulated Nylon 6 was dried overnight night at 80°C and then mixed with the specified amount of filler. The mixture was then passed through a Werner & Pfleiderer ZSK-30 twin-screw vented extruder. The extruder barrel was maintained at 235-245°C and the screw speed was maintained at 300 rpm. The extruded material was cooled and pelletized and dried at 80°C.
- [34] Test samples were then injection molded from the pelletized material using an extrusion barrel temperature of 250-270°C and a mold maintained at 70-90°C.
- [35] Three samples were made in this way: one with no filler; one with 3.15vol% of the needle-shaped boehmite of the invention; and one with 6.62vol% of the same boehmite. Figures 2A, 2B, 2C, 3A, 3B, 3C, and 4 show the UV-VIS Spectra, the FTIR spectra and the XPS, N 1s spectra of these three samples. A comparison of Figure 2A with Figures 2B and 2C shows that the nano-composite has essentially no absorption in the 400 to 700 nanometers wavelength range which corresponds to most of the visible/UV wavelength range. A comparison of Figure 3A with Figures 3B and 3C shows the effect of the boehmite on the light transmittance through a thin film of the sample. The purpose is to show the characteristic shift of the minimum encountered around 3060cm^{-1} with increasing boehmite content. This is known to relate to hydrogen bond formation and indicates clearly that hydrogen bonding between the nylon and the boehmite is at least one of the mechanisms by which the nano-dispersion of boehmite in the nylon is promoted.
- [36] Figure 4 shows the same phenomenon by means of the shift of the N 1s binding energy peak at about 400eV with increasing boehmite content.

WO 03/089508

PCT/US03/11941

- 8 -

- [37] Figure 5 shows an exfoliated surface of the product containing 6.62vol% of the boehmite particles. The image was taken using transmission electron microscopy at a magnification of X51K. From the image it can be clearly seen that the separate needle-shaped boehmite particles are uniformly and individually dispersed in the polymer with no agglomeration.

Example 3

- [38] In this Example the effect of incorporating a conventional boehmite, exemplified by C-200 available from SASOL, which has particles as shown in Figure 1A with a similar amount of the boehmite according to the invention, which has particles as shown in Figure 1B. In each case the samples evaluated were compounded as described in Example 2. The modulus of elasticity, flexural modulus, E' (storage modulus from DMA measurements) at 30°C and 135°C, tensile strength, and heat distortion temperature were measured for the unmodified nylon 6, and the same polymer with conventional boehmite and then with the boehmite according to the invention were measured. The results are presented in the bar graphs shown in Figures 6A and 6B. From these graphs it can be clearly seen that the needle-shaped boehmite outperforms the conventional boehmite and often by considerable amounts.

Example 4

- [39] In this Example the boehmite according to the invention was dispersed in an epoxy resin. The resin selected was Buehler's Epo-Kwik with its companion hardener. The boehmite used in previous examples was mixed with the resin component until homogeneous and separated into four samples. To three of the samples different surface active agents were added in an amount that was 0.5% of the weight of the boehmite in the formulation. The agents were tetraethoxysilane (TEOS); gamma-glycidoxypropyltrimethoxysilane (GPTS); and 3-aminopropyltriethoxysilane (A-1100). The fourth sample was contained no additive. The mixtures were stirred overnight on a hotplate with the temperature set between 40 and 85°C. Each mixture was then given four ultrasonic probe treatments each lasting 2.5 to 3 minutes with cooling in between each treatment in an ice bath. The samples were then placed in aluminum pans and placed under a vacuum for 20 minutes to remove air. The hardener component of the epoxy resin was then added in an amount that was one fifth of the amount of resin and

WO 03/089508

PCT/US03/11941

- 9 -

the mixture was carefully stirred and then allowed to cure overnight at room temperature. Cure was completed at 100°C at setting #4 for three hours. The cured sample was then tested to evaluate its storage modulus and the results are shown in the bar-graph presented as Figure 8 with the unmodified epoxy resin value given for the sake of comparison. As can be seen from the bar graph, the boehmite alone does not produce a great improvement but after addition of the surface active agent, the storage is raised by as much as a third.

Example 5

- [40] This example shows the effect of incorporating the boehmite of the invention in a thermoplastic polyurethane with was ISOPLAST 301 supplied by Dow Chemical Company under that trademark.
- [41] The polymer was first dried at 100°C and the needle-shaped boehmite particles prepared according to Example 1 were dried at 50°C, in each case overnight. The boehmite (1.86vol%) and the polymer were then mixed using the equipment described in Example 2 and the extrudate was cooled and pelletized. The blended pellets were then dried at 80°C and injection molded into samples for evaluation. A transmission electron micrograph showing the complete dispersal of the boehmite particles is shown at Figure 7.

WO 03/089508

PCT/US03/11941

- 10 -

CLAIMS**What Is Claimed Is:**

1. A modified polymer material comprising:
a polymer base; and
boehmite particles provided in the polymer base, the boehmite particles comprising mainly anisotropically shaped particles having an aspect ratio of at least about 3:1.
2. The material of claim 1, wherein the aspect ratio is at least about 6:1.
3. The material of claim 1, wherein the largest dimension of the boehmite particles is between about 50 and 2000 nanometers.
4. The material of claim 1, wherein the largest dimension of the boehmite particles is between about 100 and 1000 nanometers.
5. The material of claim 1, wherein the boehmite particles comprise 0.5 to 20 % volume of the modified polymer material.
6. The material of claim 1, wherein the boehmite particles comprise 2 to 10 % volume of the modified polymer material.
7. The material of claim 1, wherein the boehmite particles are free of surface agents.
8. The material of claim 1, wherein the boehmite particles are dispersed in the polymer base.
9. The material of claim 1, wherein the boehmite particles are dispersed substantially individually and uniformly in the polymer base.
10. The material of claim 9, wherein boehmite particles are substantially free of agglomerates in the polymer base.

WO 03/089508

PCT/US03/11941

- 11 -

11. The material of claim 1, wherein the polymer base comprises a thermoplastic polymer.
12. The material of claim 11, wherein the thermoplastic polymer base comprises polyamide.
13. The material of claim 12, wherein the polymer base comprises nylon
14. The material of claim 1, wherein the polymer base comprises thermosetting resin.
15. The material of claim 14, wherein the polymer base comprises at least one of a phenolic-based resin and an acrylate-based resin.
16. The material of claim 1, wherein the boehmite particles are generally directionally aligned in the polymer base.
17. The material of claim 16, wherein the modified polymer material comprises an extruded product.
18. A modified polymer material comprising:
 - a polymer base; and
 - boehmite particles free of surface agents and being dispersed in the polymer base.
19. The material of claim 18, wherein the boehmite particles are substantially uniformly and individually dispersed in the polymer base.
20. The material of claim 18, wherein the boehmite particles are substantially free of agglomerates.
21. The material of claim 18, wherein the polymer base comprises a polar polymer.
22. The material of claim 18, wherein the boehmite particles are anisotropically shaped.

WO 03/089508

PCT/US03/11941

- 12 -

23. The material of claim 22, wherein the aspect ratio is at least about 3:1.
24. A boehmite material comprising mainly boehmite particles having an aspect ratio of at least about 3:1.
25. The material of claim 24, wherein said aspect ratio is at least about 6:1.
26. The material of claim 24, wherein the largest dimension of the boehmite particles is between 50 and 2000 nanometers.
27. The material of claim 24, wherein the largest dimension of the boehmite particles is between 100 and 1000 nanometers.
28. The material of claim 24, wherein the boehmite particles have a surface area of at least 75 m²/g.
29. The material of claim 24, wherein the boehmite particles have a surface area of at least 100 m²/g.
30. A method for forming a product, comprising:
 - providing a modified polymer material comprising a polymer base and boehmite particles comprising mainly anisotropically shaped particles having an aspect ratio of at least about 3:1; and
 - extruding the modified polymer material to form an extruded product, wherein the boehmite particles are dispersed in the extruded product.
31. The method of claim 30, wherein the boehmite particles are substantially aligned in the extruded product.
32. The method of claim 30, wherein the modified polymer material is extruded into a mold to form an article.
33. The method of claim 30 wherein the polymer base comprises a thermoplastic polymer.

WO 03/089508**PCT/US03/11941****- 13 -**

34. The method of claim 33, wherein the thermoplastic polymer comprises a polyamide.
35. The method of claim 30, wherein the aspect ratio is at least about 6:1.
36. The method of claim 30, wherein the largest dimension of the boehmite particles is between 50 and 2000 nanometers.
37. The method of claim 30, wherein the boehmite particles comprise 0.5 to 20 % volume of the modified polymer material.
38. The method of claim 30, wherein the boehmite particles are dispersed substantially individually and uniformly.

WO 03/089508

PCT/US03/11941

1/7




FIG. 1A
(Prior Art)




FIG. 1B

WO 03/089508

PCT/US03/11941

2/7




FIG. 2A




FIG. 2B






FIG. 2C

WO 03/089508

PCT/US03/11941

3/7**FIG. 3A****FIG. 3B**

WO 03/089508

PCT/US03/11941

4/7




FIG. 3C




FIG. 4

WO 03/089508

PCT/US03/11941

5/7




FIG. 5




FIG. 7

WO 03/089508

PCT/US03/11941

6/7




FIG. 6A




FIG. 6B

WO 03/089508

PCT/US03/11941

7/7




FIG. 8

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 03/11941

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C08K3/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 563 653 A (YOSHIDA KOGYO KK) 6 October 1993 (1993-10-06) column 3, line 45 - line 46 claims 1-7 figure 5	1-4
X	DATABASE WPI Section Ch, Week 200212 Derwent Publications Ltd., London, GB; Class A60, AN 2002-085644 XP002250399 & JP 2001 261976 A (KAWAI SEKKAI KOGYO KK) , 26 September 2001 (2001-09-26) abstract	1
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

& document member of the same patent family

Date of the actual completion of the international search

6 August 2003

Date of mailing of the international search report

21/08/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Siemens, T

INTERNATIONAL SEARCH REPORT

Int ional Application No
PCT/US 03/11941

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Section Ch, Week 200166 Derwent Publications Ltd., London, GB; Class A60, AN 2001-586319 XP002250400 & JP 2001 180930 A (YOSHIDA KOGYO KK), 3 July 2001 (2001-07-03) abstract</p> <p>-----</p>	1

INTERNATIONAL SEARCH REPORT

Int	ional Application No
PCT/US 03/11941	

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0563653	A	06-10-1993	JP 2887023 B2	26-04-1999
			JP 5279019 A	26-10-1993
			DE 69307939 D1	20-03-1997
			DE 69307939 T2	28-08-1997
			EP 0563653 A1	06-10-1993
			KR 9705189 B1	14-04-1997
			US 5306680 A	26-04-1994
			US 5401703 A	28-03-1995
<hr/>				
JP 2001261976	A	26-09-2001	NONE	
<hr/>				
JP 2001180930	A	03-07-2001	NONE	
<hr/>				